



RIBBED BROWN KRAFT 90gsm – SUPERTACK – KRAFT 85gsm

Issue: 29/04/2021

Last Modification: 04/03/2022

Revision: 1 Page 1/1

GENERAL PRODUCT CHARACTERISTICS

Total weight 195 gsm \pm 5% ISO 536 Total caliper 197 μ m \pm 8% ISO 534

FACE

Ripped brown kraft paper, havana colour.

Substance 90 gsm \pm 3 ISO 536 Caliper 95 μ m \pm 8 ISO 534

ADHESIVE

Water emulsion acrylic based Supertack type, high initial tack and strong permanent bond for general use.

Recommended on a wide variety of substrates, including paper, board, glass, steel

Peel adhesion 16,5 N/inch \pm 2 FINAT1 Shear test 4 h \pm 2 FINAT8 Quick stick 14,4 N/inch \pm 4 FINAT9 Application temp. Range $+5^{\circ}$ C / $+40^{\circ}$ C Service temp. Range -20° C / $+90^{\circ}$ C

BACKING

One-side coated white kraft, solventless silicon coated

Substance 85 gsm \pm 3 ISO 536 Caliper 87 μ m \pm 5 ISO 534

SAFETY REGULATIONS

- The self-adhesive coating meets the European Standard EN71-3:2018 "Safety of toys / Migration of certain elements"

APPLICATIONS

Labelling on various substrates and materials where a particular graphical effect is required.

Trials are recommended, by the purchaser, on the intended substrates, prior to use, for product suitability.

PRINTABILITY

Front: excellent printing results by all common print processes, also in more than one colour.

It is always recommended asking your ink supplier to ensure best printability results.

Backing: good printing results by all common print processes, in one or more colors.

ON REQUEST

- Splits on the release paper, standard spacing 38mm or customized.
- Material certified Forest Stewardship Council® FSC-C107414

SHELF LIFE AND USE

One (1) year from delivery date when stored at the following conditions:

- Temperature +5°C/+35°C
- Relative Humidity 45% 60%
- Store in a cool dry place
- Store away from heaters or direct sunlight or rain
- Keep the sheets flat, the reels piled
- Store in the original packaging, remove packaging just before use
- Material be acclimatized at least 24 hours to ambient condition

All ITALSTICK products are subject to careful quality control throughout the production process and are warranted to be free from manufacturing defect and of quality. The reported information is based upon research and tests the Company believes to be reliable; such information does not constitute a warranty. The purchaser and/or user should carefully test, prior to use, suitability and performance of the product for the intended use and shall assume all risks for such use. ITALSTICK shall not be liable for damages beyond the replacement value of the defected product nor for incidental or consequential damages

All technical data are subject to change without prior notice.

ITALSTICK Soc. Coop. via della Stazione, 6 I-41019 Soliera www.italstick.com Ph. +39 059 566705 Fax +39 059 565127 info@italstick.com