

CF COPYFACE PAPER 57 GSM - PERMANENT - KRAFT 85 GSM

Issue: 02/12/2016 Modification:0 page 1/1

GENERAL PRODUCT CHARACTERISTICS

Total weight $160 \text{ gsm} \pm 6\%$ ISO 536 Total caliper $170 \text{ } \mu\text{m} \pm 7\%$ ISO 534

FACE

White CF paper with a special self-copying coating

Substance 57 gsm \pm 3 ISO 536 Caliper 70 μ m \pm 4 ISO 534

ADHESIVE

Water emulsion acrylic based permanent type, for application on a wide variety of surfaces such as paper, glass, steel.

Peel adhesion 15.7/inch \pm 2 FINAT1 Shear test 4h \pm 2 FINAT8 Quick stick 13.7 N/inch \pm 4 FINAT9 Min. application temp. \pm 5° C / \pm 40° C

-15°C/+80°C

BACKING

One-side coated white kraft, solventless silicon coated

Substance 85 gsm \pm 3 ISO 536 Caliper 87 μ m \pm 5 ISO 534

SAFETY REGULATIONS

Service temp. Range

- The backing paper meets the European Standard EN71-3:2013 "Safety of Toys" - Migration of certain elements

 The adhesive coating meets the FDA 21 CFR 175.105 for contact with foodstuffs and the European Standard

EN71-3:2013 "Safety of Toys" - Migration of certain elements

APPLICATIONS

To be combined with CB or CFB papers with specific treatment to obtain form sets. Recommended for shipping docs., inventory labels etc. multipart form sets where the last sheet should be self-adhesive.

Trials are recommended, by the purchaser, on the intended substrates, prior to use, for product suitability.

.

PRINTABILITY

Face: printable in offset, letterpress, flexo and silkscreen Tests for compatibility with CB and CFB papers are always recommended

Backing: good printing results by all common print processes, in one or more colors.

ON REQUEST

- Splits on the release paper, standard spacing 38mm or customized.

SHELF LIFE AND USE

One (1) year from delivery date when stored at the following conditions:

- Temperature +5°C/+35°C
- Relative Humidity 45% 60%
- Store in a cool dry place
- Store away from heaters or direct sunlight or rain
- Keep the sheets flat, the reels piled
- Store in the original packaging, remove packaging just before use
- Material to be acclimatized at least 24 hrs to ambient conditions