

WHITE OFFSET 80gsm – PERMANENT – KRAFT 85

Issue: 14/09/2011
 Modification: 0
 page 1/1

GENERAL PRODUCT CHARACTERISTICS

Total weight	182 gsm ± 5%	ISO 536
Total caliper	204 µm ± 7%	ISO 534

FACE:

White woodfree uncoated paper, high whiteness and opacity

Substance	80 gsm ± 3	ISO 536
Caliper	104 µm ± 4	ISO 534

The product meets the European Toy Regulation EN71/3

ADHESIVE

Water emulsion acrylic based permanent type, good adhesion on a wide variety of surfaces including paper, glass and steel.

Peel adhesion	15.7 N/inch ±2	FINAT1
Shear test	4h ± 2	FINAT8
Quick stick	13.7 N/inch ± 4	FINAT9
Min. application temp.	+5°C / +40°C	
Service temp. Range	-15°C/+80°C	

The adhesive complies with FDA 175.105 and BfR XIV regulations, for contact with foodstuffs.
 The product meets the European Toy Regulation EN71/3

BACKING

One-side coated white kraft, solventless silicon coated

Substance	85 gsm ± 3	ISO 536
Caliper	87µm ± 5	ISO 534

The product meets the European Toy Regulation EN71/3

APPLICATIONS

Wide range of high quality multicolor labels and stickers. Good print definition and finishing.

PRINTABILITY

Face: good printing results by all common print processes, excellent results using brilliant inks
 Backing: good printing results by all common print processes, in one or more colours.

SHELF LIFE AND USE

3 (three) years from delivery date when stored at the following conditions:

- Temperature +5°C/+35°C
- Relative Humidity 45% - 60%
- Store in a cool dry place
- Store away from heaters or direct sunlight or rain
- Keep the sheets flat, the reels piled
- Store in the original packaging

All SAM (UK) Ltd products are subject to careful quality control throughout the production process and are warranted to be free from manufacturing defect and of quality.
 The reported information is based upon research and tests the Company believes to be reliable; such information does not constitute a warranty. The purchaser and/or user should carefully test, prior to use, suitability and performance of the product for the intended use and shall assume all risks for such use. SAM shall not be liable for damages beyond the replacement value of the defected product nor for incidental or consequential damages
 All technical data are subject to change without prior notice.